

# Product Data Sheet

## DENLAKS CODEX VN-88

Version :2;ÜBF-P118

Published Date:03/2010

Page:1/3

### DESCRIPTION

Economical self-levelling cement smoothing compound for levelling and smoothing of interior surfaces.

Suitable for / on

- Producing level, fully prepared surfaces with good absorbency for textile and PVC floor coverings
- Cement screeds
- Existing surfaces with well-bonded residues of adhesive and smoothing compound

Suitable for standard smoothing work and normal wear use in domestic and commercial locations. Suitable for use on underfloor heating systems and for castor-resistance according DIN EN 15 259.

### PRODUCT PROPERTIES/BENEFITS

Plasticised dry powder cement mortar with finely graded fillers. When mixed with water, produces a hydraulic-setting smoothing compound with good flow properties and high coverage.

Composition: Special cements, mineral fillers, flow agents and additives.

- For thickness to 5-20 mm
- Excellent flow properties
- Rapid setting and readiness for covering
- Low in stresses
- High strength
- Excellent absorbency
- Low chromate content

### TECHNICAL DATA

Packaging	:paper sack
Packsize	:25 kg
Shelf life	:min. 1 year
Water quantity required	:approx. 6.0 litres per 25 kg sack
Colour	:grey
Consumption; approx	:1.5 kg /m <sup>2</sup> per mm of thickness
Working temperature	:min. 15 °C/59 °F at floor level
Working time	:60-80 minutes*
Set to foot traffic	:after 5-6 hours*
Ready for covering	:after 24 – 48 hours*

\*At 20 °C/68 °F and 65 % relative humidity

## DENLAKS CODEX VN-88

Version :2;ÜBF-P118

Published Date:03/2010

Page:2/3

### SUBSTRATE PREPARATION

The substrate must be sound, free from cracks, dry, clean and free from materials which would impair adhesion. Test the substrate according to applicable standards and report any deficiencies.

Brush, abrade, grind or shot-blast any weak surface sections or areas which will not accept adhesion. Thoroughly vacuum the surface and prime as follows:

Substrate /Use	UZIN Primer	Type
Cement screed	UZIN PE 360	D
Adhesive residue, water-resistant	UZIN PE 260	D
Adhesive residue, water-soluble	UZIN PE 460	RE
Damp cement screeds, concrete	UZIN PE 460	RE
Strengthening weak surfaces	UZIN PE 460	RE

D = Dispersion, RE = 2-component Epoxy Resin

Allow primers to dry thoroughly. Always grit-blind 2-Component Epoxy Primer-Sealer UZIN PE 460. Refer to the Product Data Sheets for other products used.

### APPLICATION

1. Put approx. 6.0 litres of cold clean water into a clean container. Sprinkle in the sack contents (25 kg) whilst stirring briskly and mix to a thick-fluid, lump-free consistency. Use a drill or mixer fitted with a UZIN Mixing Paddle. Do not mix too thinly.
2. Pour the mix onto the subfloor and distribute evenly with a smoothing trowel or rake. Where possible, apply to the desired thickness in one application. Flow and surface finish can be improved by using the UZIN Spike Roller on the wet compound.
3. Drying time at 20 °C/68 °F is approx. 24 – 48 hours. Abrading using 40 – 60 grit sanding paper improves both the surface quality and the absorbency.

### IMPORTANT NOTES

- Minimum shelf-life 1 year in original packaging and in dry storage conditions. Tightly seal opened packaging and use the contents as quickly as possible.
- Best applied at 18 – 25 °C/64 – 77 °F, floor temperature above 15 °C/59 °F and relative humidity below 75 %. Low temperatures and high humidity delays setting, drying and readiness for covering. High temperatures shorten the working time, therefore use the coldest possible mixing water during the summer.
- For applications in several layers, continue onto the still damp first layer as soon as it is set to accept traffic. Alternatively, allow the first layer to dry for 24 hours, prime with UZIN PE 60 or UZIN PE 360 and leave for 3 – 4 hours before applying the next layer.
- Protect freshly smoothed surfaces from draughts, direct sunlight and influences of heat.
- The following notices and standards are applicable and especially recommended: DIN 18 365 "Floor Covering Work".

# Product Data Sheet

## DENLAKS CODEX VN-88

Version :2;ÜBF-P118

Published Date:03/2010

Page:3/3

### PROTECTION OF THE WORKPLACE AND THE ENVIRONMENT

Contains cement low in chromate acc. Directive 2003/53/EC. Cement produces strong alkaline on reaction with water. Avoid contact with skin and eyes. In the event of contact, rinse immediately with water. In the event of skin or eye irritation, seek medical advice. When mixing wear a protective dust-mask. Use protective gloves.

Presents no physiological or ecological risk when fully cured.

Within the scope of current knowledge, gives off no emissions of formaldehyde, hazardous materials or volatile organic compounds(VOC).

Basic prerequisites for best possible indoor air quality following floor covering work are conformity to standards of the working conditions, as well as thoroughly dry substrate, primer and smoothing compound.

### DISPOSAL

Where possible, collect product residues and re-use. Do not allow dispersal into drains, sewers or ground. Empty paper bags are recyclable. Collect waste material, mix with water and allow to harden, then dispose as Construction Waste.

The above information is based on our experience and careful investigations. The variety of associated materials and different construction and working conditions cannot be individually checked or influenced by us. The quality of your work depends, therefore, on your own professional judgement and product usage. If in doubt, conduct a small test or obtain technical advice. Observe the installation recommendations of the covering manufacturer. The publication of this Product Data Sheet invalidates all previous Product Information.