

LG Hausys floors REXCOURT 8.0T

Product specification according to EN14 904

Characteristic	Standard	Unit	Result
Surface treatment			PUR(Antibacterial)
Format			Sheet
Roll Width		m	1.8
Roll Length		m	11
Total Thickness		mm	8.0
Weight		kg/m ²	4.8
Friction	NF EN 13036-4	-	Average 87
Shock absorption	EN 14808	%	≥25
Vertical deformation	EN 14809	mm	1.0
Vertical ball rebound	NF EN 12235	%	Average 99
Behaviour under a rolling load	NF EN 1569	-	No damage
Resistance to wear	EN ISO 5470-1	g	0.21
Specular gloss	EN ISO 2813	%	22
Resistance to static load	NF EN 1516	mm	Average 0.31
Resistance to impact	NF EN 1517	-	No damage
Resistance to Repeated impact	TS 15122	-	No damage
Reaction to fire	EN13501-1	-	Cfl - S1



Cfl - S1



LEED eligible under Credit
EQ4.3 for indoor Air Quality



ISO9001



ISO14001



Low Carbon
Green Growth
Korean Award