




06

STEP

| | | | |
|---|---|--|---|
| CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR | Tufted 1/10" Loop Tufté 1/10" Bouclé Getuftet 1/10" Schlinge Getuft 1/10" Luspool | FIRE RESISTANCE COMPOTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG | EN 13501-1 B _{fl} -s1 |
| PILE MATERIAL COUCHE D'USURE POLMATERIAL POOLMATERIAAL | 100% PA 6 Aqualon® | FASTNESS TO LIGHT SOLIDITÉ À LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID | ISO 105-B02 ≥5-6 |
| SECONDARY BACKING DOSSIER RÜCKENAUSSTATTUNG RUG | Back2Back: Modified bitumen enhanced with a thermoplastic elastomer, reinforced with a glass fibre fleece covered with 100% PES fleece. 10% recycled content included | RUBBING FASTNESS SOLIDITÉ AU FROTTEMENT REIBECHTHEIT WRIJFECHTHEID | EN ISO 105-X12 ≥4 |
| TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT | Ca. 4300 g/m ² | COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID | EN ISO 105-E01 ≥4 |
| PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT | Ca. 530 g/m ² | THERMAL RESISTANCE RÉSISTANCE THERMIQUE WÄRMEDURCHLABWIDERSTAND WARMTEDOORLAATWEERSTAND | ISO 8302 0,053 m ² K/W |
| PILE ABOVE BACKING POIDS DE VELOURS UTILE POLNUTZSCHICHTGEWICHT NUTTIG POOLGEWICHT | Ca. 335 g/m ² | IMPACT NOISE RATING ISOLATION PHONIQUE TRITTSCHALLVERBESSERUNGMAß GELUIDSISOLATIE | ISO 10140 ΔL: 33 dB (1 000 Hz) |
| TOTAL HEIGHT ÉPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE | Ca. 6,0 mm | SOUND ABSORPTION ABSORPTION PHONIQUE SCHALLABSORPTIONSGRAD GELUIDSABSORPTIE | ISO 354 Hz 125 250 500 1000 2000 4000 α _s 0,01 0,03 0,06 0,23 0,30 0,35 |
| PILE HEIGHT ÉPAISSEUR DU VELOURS POLDICKE POOLHOOGTE | Ca. 2,8 mm | PERMANENT ANTISTATIC ANTISTATIQUE PERMANENT PERMANENT ANTISTATISCH PERMANENT ANTISTATISCH | ISO 6356 ≤ 2 kV |
| PILE DENSITY DENSITÉ DU VELOURS POLROHDICHTE POOLDICHTHEID | Ca. 0,120 g/cm ³ | TRANSVERSAL RESISTANCE RÉSISTANCE TRANSVERSALE DURCHGANGSWIDERSTAND DOORGANGSWEERSTAND | ISO/DIS 10965 ≤ 10 ⁹ Ohm |
| TUFT DENSITY NOMBRE DE TOUFFES NOPPENZAHL AANTAL PUNTEN | Ca. 160.000 /m ² | SIZE & PACKING DIMENSION & EMBALLAGE ABMESSUNG & VERPACKUNG AFMETINGEN & VERPAKKING | 50 cm x 50 cm box: 5m ² pallet: 20 boxes |
| CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE | EN 1307 33- LC1 | NUMBER OF COLOURS NOMBRE DE COLORIS ANZAHL DER FARBEN AANTAL KLEUREN | 45, Special colours possible Coloris spéciaux possible Sonderfarben möglich Speciale kleuren mogelijk |
| CASTOR CHAIR SUITABILITY EMPLOI CHAISE À ROULETTES STUHLROLLENEIGNUNG ROLSTOELGESCHIKTHEID | EN 985 A : continuous use | DIMENSIONAL STABILITY STABILITÉ DIMENSIONNELLE DIMENSIONSTABILITÄT DIMENSIONELE STABILITEIT | EN 986 max. 0,20 % |
| DONNÉES ENVIRONNEMENTALES | Démarche HQE® : cf. FDES suivant NF P01-010 Déclaration du 30/07/2003 | GUT-NR | 23400 |
| CERTIFICATION NF-UPEC NR. DU CERTIFICATION | U.P.E.C. 329T-005.1 | BRE | ENP 428 |
| | | LEED® | Product contributes toward satisfying Credit 4.3 under LEED®. Products are not reviewed under LEED®, LEED® credit requirements cover the perfor- mance of materials in aggregate, not the performance of individual products of brands. |



modulyss®
Zevensterrestraat 21
B 9240 Zele
T +32 (0)52 45 72 11
F +32 (0)52 44 90 99
info@modulyss.com
www.modulyss.com